

09-08-00

A

UTILITY PATENT APPLICATION TRANSMITTAL <small>(Only for new nonprovisional applications under 37 CFR 1.53(b))</small>	Attorney Docket No. 208-6139
	First Inventor or Application Identifier: Verma et al.
	Title of Invention: CORROSION INHIBITING SOLUTIONS FOR ABSORPTION SYSTEMS
	Express Mail Label No. EL618191987US

ADDRESS TO: **ASSISTANT COMMISSIONER FOR PATENTS**
BOX PATENT APPLICATION
WASHINGTON, DC 20231

Transmitted herewith for filing in the United States Patent Office is a patent application for:

Inventors: Shyam Kumar Verma; George Robert Sandor

1. ☒ The Filing Fee has been calculated as shown below:

	No. Filed	No. Extra	Small Entity Rate	Fee 0	Large Entity Rate	Fee 1
BASIC FEE				\$0		\$690
TOTAL CLAIMS:	92 - 20 =	72	X 9 =	\$0	x 18 =	\$1296
INDEP CLAIMS:	14 - 3 =	11	X 39 =	\$0	x 78 =	\$858
<input type="checkbox"/> MULTIPLE DEPENDENT CLAIMS PRESENTED				+130 = \$		+260 = \$
*If the difference in Column 1 is less than zero, enter "0" in Column 2.			TOTAL \$		TOTAL \$	2844

The Commissioner is hereby authorized to credit overpayments or charge the following fees to Deposit Account No. 16-0605.

- a. ☐ Fees required under 37 CFR 1.16 (National filing fees).
b. ☒ Fees required under 37 CFR 1.17 (National application processing fees).
☐ A check in the amount of \$ ___ for the filing fee is enclosed.
- ☒ **The above filing fee will be paid along with Applicant(s) Response to the Notice to File Missing Parts.**
2. ☒ Specification; Total Pages 25
3. ☐ ___ Sheets of Formal Drawing(s) (35 USC 113)

4. ☐ Declaration and Power of Attorney; [Total Pages ____]
- a. ☐ Newly executed (original or copy)
- b. ☐ Copy from a prior application (37 CFR 1.63(d))
(for continuation/divisional with Box 16 completed)
- i. ☐ DELETION OF INVENTOR(S) Signed statement
attached deleting inventor(s) named in the prior
application, see 37 CFR 1.63(d)(2) & 1.33(b).
5. ☐ Microfiche Computer Program (Appendix)
6. ☐ Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary)
- a. ☐ Computer Readable Copy
- b. ☐ Paper Copy (identical to computer copy)
- c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

7. ☐ Assignment Papers (cover sheet & document(s) (including a check for
the \$40.00 fee)
8. ☐ 37 CFR 3.73(b) Statement (when there is an assignee); ☐ Power of Attorney
9. ☐ English Translation Document (if applicable)
10. ☐ Information Disclosure Statement (IDS)/PTO-1449; ____ Copies of IDS Citations
11. ☐ Preliminary Amendment
12. ☒ Return Receipt Postcard (MPEP 503) (Should be specifically itemized)
13. ☐ Small Entity Statement(s)
☐ Statement filed in prior application; status still proper and desired.
14. ☐ Certified Copy of Priority Document(s) (if foreign priority is claimed)
Foreign Priority is
15. ☐ Other: ____

16. **If a CONTINUING APPLICATION**, check appropriate box and supply the requisite
information below and in a preliminary amendment:

☐ Continuation ☐ Divisional ☐ Continuation in Part (CIP)
of prior Application No: ____; Filed ____

Prior Application Information: Examiner

Group/Art Unit:

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration
is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is
hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the
submitted application parts.

Table 1. Demographic characteristics of the study population	
Age (years)	Mean (SD)
18-24	20.5 (2.5)
25-34	29.5 (4.5)
35-44	39.5 (5.5)
45-54	49.5 (6.5)
55-64	59.5 (7.5)
65-74	69.5 (8.5)
75-84	79.5 (9.5)
85-94	89.5 (10.5)
95-104	99.5 (11.5)
105-114	109.5 (12.5)
115-124	119.5 (13.5)
125-134	129.5 (14.5)
135-144	139.5 (15.5)
145-154	149.5 (16.5)
155-164	159.5 (17.5)
165-174	169.5 (18.5)
175-184	179.5 (19.5)
185-194	189.5 (20.5)
195-204	199.5 (21.5)
205-214	209.5 (22.5)
215-224	219.5 (23.5)
225-234	229.5 (24.5)
235-244	239.5 (25.5)
245-254	249.5 (26.5)
255-264	259.5 (27.5)
265-274	269.5 (28.5)
275-284	279.5 (29.5)
285-294	289.5 (30.5)
295-304	299.5 (31.5)
305-314	309.5 (32.5)
315-324	319.5 (33.5)
325-334	329.5 (34.5)
335-344	339.5 (35.5)
345-354	349.5 (36.5)
355-364	359.5 (37.5)
365-374	369.5 (38.5)
375-384	379.5 (39.5)
385-394	389.5 (40.5)
395-404	399.5 (41.5)
405-414	409.5 (42.5)
415-424	419.5 (43.5)
425-434	429.5 (44.5)
435-444	439.5 (45.5)
445-454	449.5 (46.5)
455-464	459.5 (47.5)
465-474	469.5 (48.5)
475-484	479.5 (49.5)
485-494	489.5 (50.5)
495-504	499.5 (51.5)
505-514	509.5 (52.5)
515-524	519.5 (53.5)
525-534	529.5 (54.5)
535-544	539.5 (55.5)
545-554	549.5 (56.5)
555-564	559.5 (57.5)
565-574	569.5 (58.5)
575-584	579.5 (59.5)
585-594	589.5 (60.5)
595-604	599.5 (61.5)
605-614	609.5 (62.5)
615-624	619.5 (63.5)
625-634	629.5 (64.5)
635-644	639.5 (65.5)
645-654	649.5 (66.5)
655-664	659.5 (67.5)
665-674	669.5 (68.5)
675-684	679.5 (69.5)
685-694	689.5 (70.5)
695-704	699.5 (71.5)
705-714	709.5 (72.5)
715-724	719.5 (73.5)
725-734	729.5 (74.5)
735-744	739.5 (75.5)
745-754	749.5 (76.5)
755-764	759.5 (77.5)
765-774	769.5 (78.5)
775-784	779.5 (79.5)
785-794	789.5 (80.5)
795-804	799.5 (81.5)
805-814	809.5 (82.5)
815-824	819.5 (83.5)
825-834	829.5 (84.5)
835-844	839.5 (85.5)
845-854	849.5 (86.5)
855-864	859.5 (87.5)
865-874	869.5 (88.5)
875-884	879.5 (89.5)
885-894	889.5 (90.5)
895-904	899.5 (91.5)
905-914	909.5 (92.5)
915-924	919.5 (93.5)
925-934	929.5 (94.5)
935-944	939.5 (95.5)
945-954	949.5 (96.5)
955-964	959.5 (97.5)
965-974	969.5 (98.5)
975-984	979.5 (99.5)
985-994	989.5 (100.5)
995-1004	999.5 (101.5)
1005-1014	1009.5 (102.5)
1015-1024	1019.5 (103.5)
1025-1034	1029.5 (104.5)
1035-1044	1039.5 (105.5)
1045-1054	1049.5 (106.5)
1055-1064	1059.5 (107.5)
1065-1074	1069.5 (108.5)
1075-1084	1079.5 (109.5)
1085-1094	1089.5 (110.5)
1095-1104	1099.5 (111.5)
1105-1114	1109.5 (112.5)
1115-1124	1119.5 (113.5)
1125-1134	

Attention Of: Melissa B. Pendleton

Attorney/Agent of Record: Melissa B. Pendleton

ALSTON & BIRD LLP

P.O. Drawer 34009

Charlotte NC 28234-4009

Date of Deposit September 6, 2000

Grace R. Rippy

Grace R. Rippy

CORROSION INHIBITING SOLUTIONS FOR ABSORPTION SYSTEMS

CROSS REFERENCE TO RELATED APPLICATIONS

This application is related to commonly owned Provisional Application Serial No. 60/153,110, filed September 7, 1999, incorporated by reference in its entirety, and claims the benefit of its filing date under 35 USC Section 119(e).

FIELD OF THE INVENTION

This invention relates generally to corrosion inhibiting solutions, and in particular to corrosion inhibiting absorption solutions which include corrosion inhibiting agents.

BACKGROUND OF THE INVENTION

Aqueous solutions of ammonia are useful as absorbent fluids in a variety of systems, such as absorption refrigeration machines, air conditioning systems, absorption heat pumps, rectifiers, and the like. Many of these systems also include heat exchangers. These systems typically operate under anaerobic conditions at temperatures of up to 450°F. Typically such solutions include ammonia in an amount ranging from about 1 to about 50 weight percent, based on the total weight of the solution.

Aqueous solutions of alkali metal and/or alkaline earth metal hydroxides, such as solutions of calcium hydroxide, potassium hydroxide, cesium hydroxide and the like and mixtures thereof, are also used in absorbent fluids, for example in absorption cooling machines, chillers, and heat pumps. Typically such solutions include alkali metal and/or alkaline earth metal hydroxide in an amount ranging from about 20 to about 80 weight percent, based on the total weight of the solution.

Although these and other types of absorption solutions can be advantageous, aqueous ammonia, alkali metal hydroxides and/or alkaline earth metal hydroxides can be corrosive toward the materials used to construct the machines. Such materials can include mild and stainless steel for containment components and copper or copper-nickel alloys for tube bundles (typically for machines in which alkali metal hydroxide and/or alkaline earth metal hydroxide solutions are used), among others.

In addition to the surface damage caused by corrosion, the corrosion reaction evolves hydrogen gas as a byproduct. Incondensibles in the form of atoms or ions can

easily enter and diffuse into metals, resulting in the degradation of their mechanical properties under certain conditions.

The severity of corrosion can vary depending upon factors such as temperatures of the system, concentration of ammonia, alkali metal hydroxide and/or alkaline earth metal hydroxide in the absorption solution, metals used in the construction of the unit, the presence of air, and the like. For example, during use, the internal temperature of such machines can be high, typically up to about 450°F and higher, depending on the type of the absorption cycle, which can increase the corrosive effect of the solution. As noted above, corrosion can generate significant amounts of hydrogen during machine operation, which can adversely impact the performance of the machine.

Various additives, such as lithium chromate, lithium nitrate, and lithium molybdate, have been proposed as corrosion inhibitors in absorption solutions. However, lithium chromate can raise environmental concerns, and its use is being phased out. Further, the level of chromate and its oxidation state must be carefully maintained. Chromate acts as an oxidant. Thus typically large quantities of chromate are added initially and must be replaced periodically to maintain the desired level of corrosion inhibition. If too little chromate is used, then it does not properly passivate the whole metal surface and pitting can result.

Lithium nitrate can potentially evolve ammonia, which can cause stress corrosion cracking of copper based alloys such as heat exchanger tubes. Lithium molybdate exhibits only limited solubility in ammonium, alkali metal hydroxide and/or alkaline earth metal hydroxide solutions. In addition, lithium molybdate is metastable in aqueous ammonium, alkali metal hydroxide, and/or alkaline earth metal hydroxide solutions. Thus it can be difficult to maintain in aqueous ammonia, alkali metal hydroxide, and/or alkaline earth metal hydroxide solutions and to maintain a constant concentration of molybdate ions in solution.

U.S. Patent No. 5,342,578 reports the use of silicon compounds, in particular sodium silicate, as inhibitors for aqueous ammonium solutions. However, at a certain critical ammonium concentration, the effectiveness of such silicon compounds is diminished. Further, such silicon compounds can have limited solubility in an aqueous medium.

Pending U.S. Patent Application 08/882,771, filed June 26, 1997, titled "Corrosion Inhibiting Solutions for Refrigeration Systems," is directed to the use of heteropoly complex anions of transitional elements as corrosion inhibition additives. Refrigeration absorption formulations which included heteropoly complex anions as a component exhibited improved corrosion inhibition properties and low generation of hydrogen gas that is evolved due to the corrosion reaction of alkali halide solutions with the materials of construction of the refrigeration machine. Pending U.S. Patent Application Serial No. 08/896,110, filed July 17, 1997, titled "Corrosion Inhibiting Solutions for Refrigeration Systems," is directed to the use of halide compounds of metallic elements of group Va, and demonstrated that alkali halide formulations containing these elements offer improved corrosion protection and low hydrogen as compared to conventional corrosion inhibitors.

SUMMARY OF THE INVENTION

The present invention provides aqueous ammonia solutions which are useful as absorption fluids for absorption machines. In one aspect of this embodiment of the invention, the absorption solution contains at least one heteropoly complex anion of transition metal elements as a corrosion inhibitor. Alternatively the absorption solution contains a mixture of at least one heteropoly complex anion of transition metal elements with at least one other transition metal compound or salt as corrosion inhibitors. In yet another aspect of this embodiment of the invention, the absorption solution contains a mixture of at least one heteropoly complex anion with at least one compound or salt of the metallic elements of the groups IIIa to VIa of the Periodic Table of Elements as corrosion inhibitors. In yet another aspect of this embodiment of the invention, the solutions include at least one salt of a metallic element of Group Va of the Periodic Table of Elements, such as a halide or oxide thereof, and preferably antimony bromide (SbBr_3), as a corrosion inhibition additive.

Another embodiment of the invention provides alkali metal and/or alkaline earth metal hydroxide solutions, such as solutions of lithium hydroxide, calcium hydroxide, potassium hydroxide, sodium hydroxide, cesium hydroxide, and the like and mixtures thereof, which are useful as absorption fluids for absorption machines. In one aspect of this embodiment of the invention, the absorption solution contains at least one heteropoly

complex anion of transition metal elements as a corrosion inhibiting additive.

Alternatively the absorption solution contains a mixture of at least one heteropoly complex anion of transition metal elements with at least one other transition metal compound or salt as corrosion inhibitors. In yet another aspect of this embodiment of the invention, the absorption solution contains a mixture of at least one heteropoly complex anion with at least one compound or salt of the metallic elements of the groups IIIa to VIa of the Periodic Table of Elements as corrosion inhibitors. In yet another aspect of this embodiment of the invention, the solutions include at least one salt of a metallic element of Group Va of the Periodic Table of Elements, such as a halide or oxide thereof, and preferably antimony halide, as a corrosion inhibition additive.

The compositions of the invention containing the above noted corrosion inhibitors provide improved corrosion protection for the materials of construction of the absorption machine. The formulations of this invention which contain the noted additives can also provide stable formulations, thereby providing aqueous ammonia, alkali metal hydroxide and/or alkaline earth metal hydroxide solutions having a sufficient concentration of the desired corrosion inhibiting agent. In addition, the solutions can reduce hydrogen generation and thus enhance performance of the absorption machines, due to reduced accumulation of non-condensable gas in the absorber. Still further, use of the absorption solutions in an absorption machine can result in a protective layer containing magnetite (iron oxide) formed on carbon steel. The inventors have found that protective layer which forms as a result of using the solutions of the invention can be more corrosion resistant than oxide layer formed in the presence of conventional corrosion inhibitors, such as lithium molybdate, in which magnetite film tends to be more amorphous and less developed. The solutions are useful in any of the types of absorption machines known in the art, such as absorption refrigeration machines, chillers, air conditioning systems, heat exchangers, heat pump systems, and the like.


The present invention also provides processes for inhibiting corrosion of absorption machines, such as refrigeration machines, using the absorption solutions of the invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention will be described more fully hereinafter in connection with illustrative embodiments of the invention which are given so that the present disclosure will be thorough and complete and will fully convey the scope of the invention to those skilled in the art. However, it is to be understood that this invention may be embodied in many different forms and should not be construed as being limited to the specific embodiments described and illustrated herein. Although specific terms are used in the following description, these terms are merely for purposes of illustration and are not intended to define or limit the scope of the invention.

The heteropoly complex anions of transition metal elements can be generally described as coordination-type salts and free acids with a complex and high molecular weight anion. The heteropoly complex anions include as a ligand or complexing agent at least one transition metal atom which, as an ion in solution, exhibits corrosion inhibiting properties in absorption systems. The heteropoly complex anions useful in the solutions of the invention also are preferably substantially completely soluble in ammonia solution, so as to maximize the concentration of the corrosion inhibiting ions in solution. The heteropoly anions contain complexed transition metal atoms (such as Mo). Therefore, the dissolved heteropoly anions can provide a higher level of transition metal anions (Mo anions) in a solution, as compared to simple transition metal oxides, such as molybdates like lithium molybdate.

Any of the heteropoly complex anions known in the art can be used in the invention, including compounds described in the above-referenced U.S. Patent Application Serial No. 08/882,771, filed June 26, 1997, the entire disclosure of which is incorporated herein by reference. Such complexes can be generally represented by the following formulas:



wherein:

X and Z are central heteroatoms from Groups I-VIII of the Periodic Table of Elements;

the value of a varies and is 1 or 2;

5 the value of d varies and is an integer from 0 to 4;

M_bO_c , $M_bO_cH_e$, and $M_bO_c(OH)_f$ are oxoanions in which M is a transition metal element; the value of b varies, depending upon the number of transition metal atoms present in the oxoanion and can be an integer from 5 to 22, preferably 6 to 12; the value of c varies, depending upon the number of oxygen atoms present in the oxoanion attached to the transition metal and also capable of forming unique structural groups with the central atoms, and is an integer from 20 to 70, preferably from 24 to 40; the value of e varies (for example in the reduced heteropolyanion, the value of e varies depending upon the reduction of the heteropolyanion) and is an integer from 0 to 6; and the value of f varies and is an integer from 0 to 3; and

15 n is the charge of the anion and is the sum of the charges on X, Z, M, O, H, and OH.

Although the above formulas are general representations of the heteropoly complex anions useful in the invention, as will be appreciated by the skilled artisan, other compounds can also be included. Also as these formulas represent, in some heteropoly complex anions, H atoms in addition to the O atoms have been reported. Any of the various heteropoly complex anions known in the art can be used in the invention, including compounds described by G.A. Tsigdinos, Topics Curr. Chem., vol. 76, 5-64 (1978) and D.L. Kepert, Comprehensive Inorganic Chemistry (A.F. Trofman et al.) Oxford:Pergamon Press, vol. 4, pp. 607 (1973), the entire disclosure of each of which is incorporated herein by reference.

With regard to the central or heteroatom X, over 40 different elements (both metals and nonmetals) from Periodic Groups I-VIII can function as central atoms in distinct heteropoly complex anions. For example, X can be an elements selected from Groups IVB, VB, VIB, VIIB, VIII, IB, IIB, IIIA, IVA, and VA of the Periodic Table of Elements. Exemplary central atoms include, but are not limited to, ions of phosphorus, silicon, manganese, arsenic, boron, iron, tellurium, copper, zinc, aluminum, tin,

zirconium, titanium, vanadium, antimony, bismuth, chromium, gallium, germanium, and the like.

M is a 2-18 hexavalent transition metal element atom, which surrounds one or more central atoms X. The transition metal atom M is selected from those elements which as ions in solution provide corrosion inhibiting effect in absorption systems. Preferably the transition metal element M in the oxoanion is derived from molybdate or tungstate. Other transition metal elements can also be present, as represented in the formula as Z, such as but not limited to, an element selected from Groups IVB, VB, VIB, VIIB, VIII, IB, IIB, IIIA, IVA, and VA of the Periodic Table of Elements. Exemplary elements include without limitation manganese, cobalt, nickel, copper, zinc, vanadium, niobium, tantalum, gallium, germanium, arsenic, antimony, bismuth, tellurium, and the like and other transition elements.

Exemplary heteropoly complex anions include, but are not limited to, phosphomolybdates, such as but not limited to, $[\text{PMo}_{12}\text{O}_{40}]^{-3}$, wherein P^{+5} is the central atom or heteroatom, $[\text{PMo}_{10}\text{V}_2\text{O}_{40}]^{-5}$, and the like; silicon molybdates, such as but not limited to, $[\text{SiMo}_{11}\text{NiO}_{40}\text{H}_2]^{-6}$, wherein Si^{+4} is the central atom; manganese molybdates, such as but not limited to, $[\text{MnMo}_9\text{O}_{32}]^{-6}$, wherein Mn^{+4} is the central atom; silicon tungstates, such as but not limited to, $[\text{SiW}_{12}\text{O}_{40}]^{-4}$, wherein Si^{+4} is the central atom; tellurium molybdates, such as but not limited to, $[\text{TeMo}_6\text{O}_{24}]^{-6}$, wherein Te^{+6} is the central atom; arsenic molybdates, such as but not limited to, $[\text{As}_2\text{Mo}_{18}\text{O}_{62}]^{-6}$, wherein As^{+5} is the central atom; manganese niobates, such as but not limited to, $[\text{MnNb}_{12}\text{O}_{36}]^{12}$, wherein Mn^{+4} is the central atom; and the like, and mixtures thereof. Currently preferred heteropoly complex anions are phosphomolybdates.

The heteropoly complex anions which have been structurally characterized can be divided into the broad groups, depending upon the heteroatom [X], transition metal atom [M] stoichiometry, and upon the coordination number of the heteroatom (that is, the number of points at which M is attached to the heteroatom in the complex). The heteropoly complex anions can be classified according to the ratio of the number of the central atoms to the peripheral molybdenum or other such atoms. For example, the different types of known heteropoly complex anions of molybdate show the following X:M ratio with one or more central atoms: X:M = 1:12, 1:11, 1:10, 1:9, 1:6, 2:10, 2:17,

2:5, 4:12, 1m:6m (m unknown) and 1:1 heteropoly complex anions. The known tungstates include all of the above in addition to 2:18, 2:17 and 2:4:18.

In a preferred embodiment of the invention, the transition metal of the heteropoly complex anion is molybdenum or tungsten, and more preferably molybdenum. A particularly preferred solution includes the heteropoly complex anion $[\text{PMo}_{12}\text{O}_{40}]^{-3}$.

Transition metal compounds or salts useful in the invention are selected from compounds of transition metals which are capable of providing the transition metal element as ions in aqueous ammonia solution for complexing with the chosen heteropoly anion. The transition metal element of the transition metal compound can be the same or different from the transition metal of the heteropoly anion complex. Exemplary transition metal compounds or salts include nitrates, halides, oxides, and the like, preferably a halide, of the transition metal elements such as cobalt, nickel, tungsten, zirconium, manganese, chromium, and the like, and mixtures thereof.

The compounds or salts of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements are also selected from compounds which are capable of providing the metallic elements of Group IIIa to VIa as ions in ammonium solutions. Exemplary compounds or salts of the metallic elements of Groups IIIa to VIa include oxides, sulfides, halides, nitrates, and the like, preferably a halide, of metallic elements of Group IIIa to VIa, such as antimony, germanium, and the like. For example, the above-referenced U.S. Patent Application Serial No. 08/896,110, filed July 17, 1997, describes halides of metallic elements of Group Va of the Periodic Table of Elements which can be useful in the invention, although other compounds can also be useful in this invention. Exemplary halides of Group Va metallic elements (i.e., arsenic, antimony, and bismuth) include antimony bromide, arsenic bromide, and bismuth bromide, and the like and mixtures thereof. The entire disclosure of pending U.S. Application Serial No. 08/896,110, filed July 17, 1997, is incorporated herein by reference.

Salts of the Group Va metallic elements (i.e., arsenic, antimony, and bismuth) can include, for example, oxides and halides, such as bromide, chloride, or iodide, and preferably is bromide. Exemplary halides of Group Va metallic elements useful as corrosion inhibiting agents in the absorption solutions of the invention include antimony bromide (SbBr_3), arsenic bromide, and bismuth bromide, and the like and mixtures

thereof. These Group Va metallic elements as ions in solution can exhibit corrosion inhibiting properties in absorption refrigeration systems.

The heteropoly complex anions, transition metal compounds, compounds of metallic elements of Groups IIIa and VIa, and salts of Group Va metallic elements are present in the compositions of the invention in amounts sufficient to provide the desired corrosion inhibiting effect. This amount can vary depending upon various factors, such as the solubility of the compounds in the absorption solution, the nature of the ions, temperatures in the machine, concentration of ammonia in aqueous solution, alkali metal hydroxides and/or alkaline metal hydroxides in solution, metals used in the construction of the unit, the presence of air, and the like. Preferably, the absorption solutions of the invention include at least one heteropoly complex anion in an amount ranging from about 100 parts per million (ppm) to about 3000 ppm, more preferably about 200 ppm to about 800 ppm. Transition metal compounds or compounds of the metallic elements of Group IIIa to VIa can be present in the solutions in amounts ranging from about 10 parts per million (ppm) to about 3000 ppm. Salts of metallic elements of Group Va can be present in an amount ranging from about 10 parts per million (ppm) to about 5000 ppm, and preferably from about 150 ppm to about 400 ppm. The corrosion inhibiting agents can also be useful in amounts outside of these ranges, so long as the agent is present in an amount sufficient to provide corrosion inhibition properties.

The aqueous ammonium absorption solution can include ammonia in conventional amounts. An exemplary solution includes ammonia in an amount from about 1 to about 50 weight percent, preferably about 5 to about 50 weight percent, based on the total weight of the solution, although as the skilled artisan will appreciate, amounts outside of this range can be used as well.

The alkali metal hydroxide and/or alkaline earth metal hydroxide absorption solutions can include alkali metal hydroxides, alkaline earth metal hydroxides and mixtures of alkali metal hydroxides and alkaline earth metal hydroxides in conventional amounts. An exemplary alkali metal and/or alkaline earth metal hydroxide absorption solution includes alkali metal and/or alkaline earth metal hydroxide in an amount from about 20 to about 80 weight percent, preferably about 10 to about 70 weight percent, based on the total weight of the solution, although as the skilled artisan will appreciate,

amounts outside of this range can be used as well. The alkali metal and/or alkaline earth metal hydroxide can be, for example, calcium hydroxide, potassium hydroxide, cesium hydroxide and the like and mixtures thereof.

Further, the absorption solution can include lithium nitrate, molybdate and/or chromate in conventional amounts. Still further, the absorption solution can include halides, such as zinc halides, which can be particularly useful in high temperature applications (generally about 450°F and higher). The zinc halides can be present in amounts up to about 50 weight percent.

The present invention also provides processes for inhibiting the corrosion of an absorption machine (such as a refrigeration machines) resulting from the presence of aqueous ammonium, alkali metal hydroxide and/or alkaline earth metal hydroxide absorbent solutions. In the process of the invention, the above described aqueous ammonia, alkali metal hydroxide and/or alkaline earth metal hydroxide solutions which include at least one heteropoly anion complex, or a mixture of the heteropoly anion complex with a transition metal compound or a compound of the metallic elements of Groups IIIa to VIa, or a halide of a metallic element of Group Va of the Periodic Table of Elements is circulated in an absorption machine under conditions and in amounts sufficient to provide a corrosion inhibiting effect. As the skilled artisan will appreciate, the environment or conditions, such as temperature and/or pressure, of different refrigeration machines can vary. Typically, the temperature of the machine can be as high as 550°F, and higher. The solutions are particularly advantageous for high temperature applications.

The present invention will be further illustrated by the following non-limiting examples.

Example

Aqueous ammonium solutions (3%) having different corrosion inhibitors were prepared. Sodium chromate was the corrosion inhibitor in one solution. Sodium chromate is a corrosion inhibitor conventionally used in such machines. Solutions in accordance with the present invention including the heteropoly complex anion

phosphomolybdic acid (PMA) and this complex in combination with an antimony halide [Note to Shyam – did you use] were also prepared.

The solutions were tested to determine the effectiveness of the corrosion inhibitors. Specifically tests were performed in a pressure vessel autoclave with temperature control of (+/- 2°F). The solutions used in the tests were prepared as 3% ammonia concentration. The alkalinity of the solutions was adjusted with lithium hydroxide to control the solution pH at a level that optimized the performance of each chemical or generally accepted in the industry.

Pre-weighed metal coupons of C1018 carbon steel were placed in and above the solution contained in a 2 liter cylinder made of inconel-600 material which fits into the furnace. In order to eliminate the air from the headspace, the cylinder containing the solution was evacuated using a vacuum pump prior to starting the test. The solution was heated to 400°F and held at this temperature for a period of 168 hours.

Upon completion, the test coupons were removed and cleaned by ASTM method G1-90. The corrosion rate was calculated from the weight loss. The level of hydrogen generated during the test was also determined at the end of each test. The results are set forth in Table 1 below.

Table 1
Corrosion rate of carbon steel in aqua-ammonia solution
(3% ammonia solution) at 400°F in one week.

Additive	Corrosion rate (mils per year) for carbon steel in		Hydrogen generated mg/in ² /week	Surface evaluation
	Liquid	Vapor		
Sodium chromate (2000 ppm)	2.08	3.16	0.99	Crevice and pitting corrosion in liquid or vapor
PMA (300 ppm)	2.00	2.77	0.48	No crevice or pitting corrosion. Excellent protection in liquid and vapor
PMA/Sb complex (400 ppm)	0.25	0.20	0.93	No crevice or pitting corrosion. Excellent protection in liquid and vapor

That Which Is Claimed Is:

1. An absorption solution comprising aqueous ammonia and at least one heteropoly complex anion of a transition metal element present in an amount sufficient to provide a corrosion inhibiting effect.

5 2. The solution of Claim 1, said solution further comprising at least one additional additive in an amount sufficient to provide a corrosion inhibiting effect.

3. The solution of Claim 1, wherein said at least one heteropoly complex anion comprises at least one transition metal atom having corrosion inhibiting properties in absorption refrigeration systems.

10 4. The solution of Claim 1, wherein said at least one heteropoly complex anion comprises a compound selected from the group consisting of $[X_aM_bO_c]^{-n}$, $[X_aZ_dM_bO_c]^{-n}$, $[X_aZ_dM_bO_cH_e]^{-n}$, $[X_aM_bO_c(OH)_f]^{-n}$, $[X_aZ_dM_bO_c(OH)_f]^{-n}$, and mixtures thereof, wherein:

15 X and Z are central heteroatoms selected from the group consisting of elements from Groups I-VIII of the Periodic Table of Elements;

a is 1 or 2;

d is an integer from 0 to 4;

20 M_bO_c , $M_bO_cH_e$, and $M_bO_c(OH)_f$ are oxoanions in which M is a transition metal element; b is an integer from 5 to 22; c is an integer from 20 to 70; e is an integer from 0 to 6; and f is an integer from 0 to 3; and

n is the charge of the anion.

5. The solution of Claim 4, wherein:

X is phosphorus, silicon, manganese, tellurium or arsenic; and

M is molybdenum or tungsten.

25 6. The solution of Claim 1, wherein said at least one heteropoly complex anion is selected from the group consisting of phosphomolybdates, silicon molybdates, manganese molybdates, silicon tungstates, tellurium molybdates, arsenic molybdates, and mixtures thereof.

7. The solution of Claim 1, wherein said at least one heteropoly complex anion comprises a phosphomolybdate of the formula $[\text{PMo}_{12}\text{O}_{40}]^{-3}$.

8. The solution of Claim 2, wherein said at least one additional additive comprises at least one transition metal compound.

5 9. The solution of Claim 8, wherein said at least one transition metal compound is selected from compounds of transition metals which are capable of providing the transition metal element as ions in aqueous ammonia.

10 10. The solution of Claim 8, wherein said at least one transition metal compound comprises a transition metal which is different from the transition metal of the heteropoly anion complex.

11. The solution of Claim 8, wherein said at least one transition metal compound comprises a salt of a transition metal element.

15 12. The solution of Claim 11, wherein said salt comprises a compound selected from the group consisting of nitrates, halides, and oxides of transition metal elements, and mixtures thereof.

13. The solution of Claim 11, wherein said transition metal is selected from the group consisting of cobalt, nickel, tungsten, zirconium, manganese, chromium, and mixtures thereof.

20 14. The solution of Claim 11, wherein said salt is a halide of a transition metal element.

15. The solution of Claim 2, wherein said at least one additional additive comprises at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements.

25 16. The solution of Claim 15, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises a

compound capable of providing the metallic elements of Group IIIa to VIa as ions in alkali metal halide solutions.

17. The solution of Claim 15, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises at least one salt of a metallic element of Group IIIa to VIa.

18. The solution of Claim 17, wherein said salt comprises a compound selected from the group consisting of oxides, sulfides, halides, nitrates, and mixtures thereof of metallic elements of Group IIIa to VIa.

19. The solution of Claim 17, wherein said salt comprises a halide of a metallic element of Groups IIIa to VIa.

20. The solution of Claim 17, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises antimony as the metallic element of Groups IIIa to VIa.

21. The solution of Claim 17, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises a compound selected from the group consisting of antimony bromide, germanium bromide, arsenic bromide, and bismuth bromide, and mixtures thereof.

22. The solution of Claim 1, wherein ammonia is present in an amount from about 1 to about 50 weight percent, based on the total weight of the solution.

23. An absorption solution for refrigeration systems, comprising aqueous ammonia, at least one heteropoly complex anion of a transition metal element, and at least one additional additive comprising a compound selected from the group consisting of transition metal salts, salts of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements, and mixtures thereof, said at least one heteropoly complex anion of a transition metal element and said at least one additional additive present in an amount sufficient to provide a corrosion inhibiting effect.

24. The solution of Claim 23, wherein said at least one heteropoly complex anion of a transition metal element comprises a phosphomolybdate, and said least one additional additive comprises at least one transition metal salt.

25. The solution of Claim 24, wherein said at least one transition metal salt comprises at least one halide of cobalt, nickel, tungsten, zirconium, manganese, chromium, and mixtures thereof.

26. The solution of Claim 23, wherein said at least one heteropoly complex anion of a transition metal element comprises a phosphomolybdate and said at least one additional additive comprises at least one salt of a metallic element of Group IIIa to VIa.

27. The solution of Claim 26, wherein said at least one salt comprises a halide of the metallic elements of Group Va of the Periodic Table of Elements.

28. The solution of Claim 27, wherein said halide comprises a compound selected from the group consisting of antimony bromide (SbBr_3), arsenic bromide, bismuth bromide and mixtures thereof.

29. The solution of Claim 23, wherein said at least one heteropoly complex anion of a transition metal element is $[\text{PMo}_{12}\text{O}_{40}]^{-3}$.

30. The solution of Claim 23, wherein ammonia is present in an amount from about 1 to about 50 weight percent, based on the total weight of the solution.

31. An absorption solution for refrigeration systems, comprising at aqueous ammonia, at least one phosphomolybdate, and at least one transition metal halide, said phosphomolybdate and said transition metal halide present in an amount sufficient to provide a corrosion inhibiting effect.

32. The solution of Claim 31, wherein said phosphomolybdate is $[\text{PMo}_{12}\text{O}_{40}]^{-3}$, and said transition metal halide is cobalt halide or nickel halide.

33. The solution of Claim 31, wherein ammonia is present in an amount from about 1 to about 50 weight percent, based on the total weight of the solution.

34. An absorption solution for refrigeration systems, comprising aqueous ammonia, at least one phosphomolybdate, and at least one halide of the metallic elements of Group Va of the Periodic Table of Elements, said phosphomolybdate and said halide present in an amount sufficient to provide a corrosion inhibiting effect.

5 35. The solution of Claim 34, wherein said phosphomolybdate is $[\text{PMo}_{12}\text{O}_{40}]^3$, and said halide is antimony bromide (SbBr_3).

36. The solution of Claim 34, wherein ammonia is present in an amount from about 1 to about 50 weight percent, based on the total weight of the solution.

10 37. A process for inhibiting the corrosion of a machine resulting from the presence of absorbent solutions comprising aqueous ammonia, the process comprising circulating in a machine said absorption solution comprising aqueous ammonia and at least one heteropoly complex anion of a transition metal element, said at least one heteropoly complex anion of a transition metal element present in an amount sufficient to provide a corrosion inhibiting effect.

15 38. The process of Claim 37, wherein said solution further comprises at least one additional additive comprising a compound selected from the group consisting of transition metal compounds, compounds of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements, and mixtures thereof, said at least one additional additive present in an amount sufficient to provide a corrosion inhibiting effect.

20 39. The process of Claim 37, wherein during said circulating step, said at least one heteropoly complex anion forms a protective layer on a surface within said machine.

40. The process of Claim 37, wherein during said circulating step said solution is exposed to temperatures ranging from about 150°F to about 550°F.

25 41. The process of Claim 37, wherein said absorbent solution further comprises lithium nitrate and zinc halide.

42. The process of Claim 37, wherein ammonia is present in an amount from about 1 to about 50 weight percent, based on the total weight of the solution.

43. An absorption solution comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof and at least one heteropoly complex anion of a transition metal element present in an amount sufficient to provide a corrosion inhibiting effect.

44. The solution of Claim 43, further comprising at least one additional additive in an amount sufficient to provide a corrosion inhibiting effect.

45. The solution of Claim 43, wherein said at least one heteropoly complex anion comprises at least one transition metal atom having corrosion inhibiting properties in absorption refrigeration systems.

46. The solution of Claim 43, wherein said at least one heteropoly complex anion comprises a compound selected from the group consisting of $[X_aM_bO_c]^{-n}$, $[X_aZ_dM_bO_c]^{-n}$, $[X_aZ_dM_bO_cH_e]^{-n}$, $[X_aM_bO_c(OH)_f]^{-n}$, $[X_aZ_dM_bO_c(OH)_f]^{-n}$, and mixtures thereof, wherein:

X and Z are central heteroatoms selected from the group consisting of elements from Groups I-VIII of the Periodic Table of Elements;

a is 1 or 2;

d is an integer from 0 to 4;

M_bO_c , $M_bO_cH_e$, and $M_bO_c(OH)_f$ are oxoanions in which M is a transition metal element; b is an integer from 5 to 22; c is an integer from 20 to 70; e is an integer from 0 to 6; and f is an integer from 0 to 3; and

n is the charge of the anion..

47. The solution of Claim 46, wherein:

X is phosphorus, silicon, manganese, tellurium or arsenic; and

M is molybdenum or tungsten.

48. The solution of Claim 43, wherein said at least one heteropoly complex anion is selected from the group consisting of phosphomolybdates, silicon molybdates,

manganese molybdates, silicon tungstates, tellurium molybdates, arsenic molybdates, and mixtures thereof.

49. The solution of Claim 43, wherein said at least one heteropoly complex anion comprises a phosphomolybdate of the formula $[\text{PMo}_{12}\text{O}_{40}]^{-3}$.

5 50. The solution of Claim 49, wherein said at least one additional additive comprises at least one transition metal compound.

51. The solution of Claim 50, wherein said at least one transition metal compound is selected from compounds of transition metals which are capable of providing the transition metal element as ions in solution of alkali metal hydroxide, alkaline earth metal hydroxide, and mixtures thereof.

52. The solution of Claim 51, wherein said at least one transition metal compound comprises a transition metal which is different from the transition metal of the heteropoly anion complex.

53. The solution of Claim 50, wherein said at least one transition metal compound comprises a salt of transition metal element.

54. The solution of Claim 53, wherein said salt comprises a compound selected from the group consisting of nitrates, halides, and oxides of transition metal elements, and mixtures thereof.

55. The solution of Claim 53, wherein said transition metal is selected from the group consisting of cobalt, nickel, tungsten, zirconium, manganese, chromium, and mixtures thereof.

56. The solution of Claim 53, wherein said salt comprises a halide of a transition metal element.

57. The solution of Claim 44, wherein said at least one additional additive comprises at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements.

58. The solution of Claim 57, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises a compound capable of providing the metallic elements of Group IIIa to VIa as ions in alkali metal halide solutions.

5 59. The solution of Claim 58, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises at least one salt of a metallic element of Group IIIa to VIa.

60. The solution of Claim 59, wherein said salt comprises a compound selected from the group consisting of oxides, sulfides, halides, nitrates, and mixtures thereof of metallic elements of Group IIIa to VIa.

61. The solution of Claim 59, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises a halide of a metallic element of Groups IIIa to VIa.

62. The solution of Claim 59, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises antimony as the metallic element of Groups IIIa to VIa.

63. The solution of Claim 59, wherein said at least one compound of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements comprises a compound selected from the group consisting of antimony bromide, germanium bromide, arsenic bromide, and bismuth bromide, and mixtures thereof.

64. The solution of Claim 43, wherein said alkali metal hydroxide, alkaline earth metal hydroxide or mixture thereof is present in an amount from about 20 to about 80 weight percent, based on the total weight of the solution.

65. An absorption solution for refrigeration systems, comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof, at least one heteropoly complex anion of a transition metal element, and at least one additional additive comprising a compound selected from the group consisting of transition metal

salts, salts of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements, and mixtures thereof, said at least one heteropoly complex anion of a transition metal element and said at least one additional additive present in an amount sufficient to provide a corrosion inhibiting effect.

5 66. The solution of Claim 65, wherein said at least one heteropoly complex anion of a transition metal element comprises a phosphomolybdate, and said least one additional additive comprises at least one transition metal salt.

67. The solution of Claim 66, wherein said at least one transition metal salt comprises at least one halide of cobalt, nickel, tungsten, zirconium, manganese,
10 chromium, and mixtures thereof.

68. The solution of Claim 65, wherein said at least one heteropoly complex anion of a transition metal element comprises a phosphomolybdate and said at least one additional additive comprises at least one salt of a metallic element of Group IIIa to VIa.

69. The solution of Claim 68, wherein said at least one salt comprises an oxide
15 or halide of the metallic elements of Group Va of the Periodic Table of Elements.

70. The solution of Claim 69, wherein said halide comprises antimony bromide (SbBr_3), arsenic bromide, or bismuth bromide.

71. The solution of Claim 65, wherein said at least one heteropoly complex anion of a transition metal element is $[\text{PMo}_{12}\text{O}_{40}]^{-3}$.

20 72. The solution of Claim 65, wherein said alkali metal hydroxide, alkaline earth metal hydroxide or mixture thereof is present in an amount from about 20 to about 80 weight percent, based on the total weight of the solution.

73. An absorption solution for refrigeration systems, comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof, at least one
25 phosphomolybdate, and at least one transition metal halide, said phosphomolybdate and said transition metal halide present in an amount sufficient to provide a corrosion inhibiting effect.

74. The solution of Claim 73, wherein said phosphomolybdate is $[\text{PMo}_{12}\text{O}_{40}]^{3-}$, and said transition metal halide is cobalt halide or nickel halide.

75. The solution of Claim 73, wherein said alkali metal hydroxide, alkaline earth metal hydroxide or mixture thereof is present in an amount from about 20 to about 80 weight percent, based on the total weight of the solution.

76. An absorption solution for refrigeration systems, comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof, at least one phosphomolybdate, and at least one halide of the metallic elements of Group Va of the Periodic Table of Elements, said phosphomolybdate and said halide present in an amount sufficient to provide a corrosion inhibiting effect.

77. The solution of Claim 76, wherein said phosphomolybdate is $[\text{PMo}_{12}\text{O}_{40}]^{3-}$, and said halide is antimony bromide (SbBr_3).

78. The solution of Claim 76, wherein said alkali metal hydroxide, alkaline earth metal hydroxide or mixture thereof is present in an amount from about 20 to about 80 weight percent, based on the total weight of the solution.

79. A process for inhibiting the corrosion of a machine resulting from the presence of absorbent solutions comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof, the process comprising circulating in a machine said absorption solution comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof, and at least one heteropoly complex anion of a transition metal element in an amount sufficient to provide a corrosion inhibiting effect.

80. The process of Claim 79, wherein said solution further comprises at least one additional additive comprising a compound selected from the group consisting of transition metal compounds, compounds of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements, and mixtures thereof in an amount sufficient to provide a corrosion inhibiting effect.

81. The process of Claim 79, wherein during said circulating step, said at least one heteropoly complex anion forms a protective layer on a surface within said machine.

82. The process of Claim 79, wherein during said circulating step said solution is exposed to temperatures ranging from about 150°F to about 550°F.

83. The process of Claim 79, wherein said absorbent solution further comprises lithium nitrate and zinc halide.

84. The solution of Claim 79, wherein said alkali metal hydroxide, alkaline earth metal hydroxide or mixture thereof is present in an amount from about 20 to about 80 weight percent, based on the total weight of the solution.

85. An absorption solution for refrigeration systems, comprising aqueous ammonia and at least one halide of a Group Va metallic element in an amount sufficient to provide a corrosion inhibiting effect.

86. The solution of Claim 85, wherein said at least one halide of a Group Va metallic element comprises antimony bromide (SbBr_3).

87. The solution of Claim 85, wherein said at least one Group Va metallic element is present as halide in an amount of about 10 ppm to about 3000 ppm.

88. A process for inhibiting the corrosion of a machine resulting from the presence of aqueous ammonium absorbent solutions, comprising circulating in a machine an absorption solution comprising ammonium and at least one halide of a Group Va metallic element in an amount sufficient to provide a corrosion inhibiting effect.

89. An absorption solution for refrigeration systems, comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof and at least one halide of a Group Va metallic element in an amount sufficient to provide a corrosion inhibiting effect.

90. The solution of Claim 89, wherein said at least one halide of a Group Va metallic element comprises antimony bromide (SbBr_3).

91. The solution of Claim 89, wherein said at least one Group Va metallic element is present as halide in an amount of about 10 ppm to about 3000 ppm.

92. A process for inhibiting the corrosion of a machine resulting from the presence of alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof
5 absorbent solutions, comprising circulating in a machine an absorption solution comprising at least one alkali metal hydroxide, alkaline earth metal hydroxide, or a mixture thereof and at least one halide of a Group Va metallic element in an amount sufficient to provide a corrosion inhibiting effect.

003060 "5459560

CORROSION INHIBITING SOLUTIONS FOR ABSORPTION SYSTEMS

ABSTRACT OF THE DISCLOSURE

Anti-corrosion solutions and processes useful for refrigeration processes are disclosed. Heteropoly complex anions of transitional metal elements can be added to an absorption solution which includes aqueous ammonia, alkali metal hydroxide and/or
5 alkaline earth metal hydroxide, optionally in combination with transition metal compounds or compounds of the metallic elements of Groups IIIa to VIa of the Periodic Table of Elements to minimize corrosion of systems within which the solution is used.

CLT01/4441095v1